

Filter stable drainage system

Secudrain® 131 C WD 401 131 C



NAUE GmbH & Co. KG
Gewerbestrasse 2
32339 Espelkamp-Fiestel, Germany

Phone: +49 5743 41-0 · Fax: +49 5743 41-240
E-Mail: info@naue.com · Internet: www.naue.com

Product description

Three-layered, three-dimensional, filter stable and high compression resistance drainage system consisting of an extruded wave-shaped monofilament core and a needle-punched nonwoven fully bonded at on both sides

Property	Test method*	Unit	131 C WD 401 131 C
Total product	-	-	
Water flow rate q , $md_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa - at a load of 100 kPa	EN ISO 12958	$l/(m \times s)$	$i = 0.1$ 2.5×10^{-1} $i = 0.1$ 2.0×10^{-1} $i = 0.1$ 1.5×10^{-1}
Water flow rate q , $md_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa - at a load of 100 kPa			$i = 0.3$ 5.0×10^{-1} $i = 0.3$ 4.0×10^{-1} $i = 0.3$ 3.0×10^{-1}
Water flow rate q , $md_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa - at a load of 100 kPa			$i = 1.0$ $1.0 \times 10^{+0}$ $i = 1.0$ 9.0×10^{-1} $i = 1.0$ 8.0×10^{-1}
Mass per unit area	EN ISO 9864	g/m^2	660
Thickness	EN ISO 9863-1	mm	approx. 6.5
Max. tensile strength, md / cmd^{**}	EN ISO 10319	kN/m	15.0 / 15.0
Elongation at max. tensile strength, md / cmd^{**}	EN ISO 10319	%	40 / 40
Puncture force	EN ISO 12236	kN	3.0
Raw material	-	-	polypropylene
Geotextiles	131 C / 131 C	-	
Mass per unit area	EN ISO 9864	g/m^2	130
Thickness	EN ISO 9863-1	mm	0.7
Characteristic Opening Size	EN ISO 12956	mm	0.08
Water permeability - VI_{H50} -Index - Flow rate c_{H50}	EN ISO 11058	m/s l/sm^2	9.0×10^{-2} 90
Roll dimension, width x length	-	m x m	3.80 x 70

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.