

Leakdrain S6U STD

GEOSYNTHETIC SOLUTIONS **



Fibertex
SOUTH AFRICA

Leakdrain S6U STD consists of a single cusped HDPE (High Density Polyethylene) high performance core. The core has the necessary compressive strength and in-plane flow capacity required to conduct leachate and other particle laden liquids without clogging. The core design has flat surfaces to provide protection and minimal stresses on the surrounding surfaces. Its main application is as a leak detection layer between two geomembrane at the base in containment systems.

SPECIFICATIONS

Physical Properties:						
Colour		Black				
Type		Single Cuspated (Dimpled)				
Material		HDPE (High Density Polyethylene)				
Mass per unit area	(g/m²)	700			EN ISO 9864	
Equivalent sheet thickness	(mm)	0.75				
Dimple height	(mm)	6.6			EN ISO 9863-1	
Dimple centres	(mm)	8.0				
Height of Flow Path	(mm)	5.4				
Surface contact - top	(%)	10				
Surface contact - bottom	(%)	60				
Performance:						
Carbon Black Content	(%)	0.8 – 2.5			ASTM D1603:94	
Tensile Strength (MD/CD)	(kN/m)	7 / 5			EN ISO 10319	
Elongation (MD/CD)	(%)	50 / 35			EN ISO 10319	
CBR puncture resistance	(N)	900			EN ISO 12236	
Compressive strength	(kPa)	250			ASTM D1621 (mod)	
<u>In-plane water flow</u>		<u>HG=1.0</u>		<u>HG=0.1</u>	<u>Hydraulic Gradient</u>	
At 20 kPa pressure	(l/m.sec)	2.65	±0.15	0.80	±0.15	EN ISO 12958
At 100 kPa pressure	(l/m.sec)	2.50	±0.15	0.75	±0.15	EN ISO 12958
At 200 kPa pressure	(l/m.sec)	2.40	±0.15	0.70	±0.15	EN ISO 12958
At 500 kPa pressure	(l/m.sec)	2.00	±0.15	0.57	±0.15	
With hard platen boundary conditions to simulate installation on rigid surfaces						
Life expectancy	(yrs)	120 (manufacturers declaration)				
Working Temperature	(°C)	-20 to 80				
Chemical resistance		Excellent resistance to all common chemicals				
Resistance to microbes		No significant effect				
Compatibility with geomembranes		Fully compatible. All components compatible with potable water				
Slope Stability		Data Available on request				
Health, safety, environment		INERT. No known health hazard. No precautions necessary.				

Cont/...Page 2

The information contained in this publication is provided in good faith and to the best of our knowledge is true and accurate.
Fibertex South Africa reserves the right to make technical modifications to their products without notice.



KZN: (T) +27 (0)31 736 7100
(E) salesza@fibertex.com

GAUTENG: (T) +27 (0)11 965 0205
(E) tenders@geotextilesafrica.co.za

W CAPE: (T) +27 (0)21 701 3569
(E) adminct@geotextilesafrica.co.za

www.fibertex.com / www.geotextilesafrica.co.za

** GEOTEXTILES • GEOGRIDS • SUBSOIL DRAINAGE PIPE & FITTINGS • GEOCELLS • COMPOSITE DRAINAGE SYTEMS • GABIONS & MATTRESSES
• CUSPATED SHEETS • GEOBAGS • GCLs • GEOMEMBRANE

Roll Dimensions:

Roll Width & Length	(mm)	2.2 x 100
Roll weight and diameter	(kg, m)	155, 0.83 with 100mm ID tube
Overlap & Wastage allowance	(%,%)	2%, 1-5% depending on the shape of the area to be covered

Notes:

1. The values given are indicative and correspond to nominal results obtained in the manufacturer's laboratories and testing institutes.
2. Please note soft platen performance at pressures in excess of 200 kPa is outside EN ISO 12958.
3. The product will continue to perform well under short term loading in excess of 500 kPa. Please request details.
4. Unless otherwise stated allowable tolerances are $\pm 10\%$ of the typical value. The tolerance on roll length is 1.5% and on roll width is 1.0%.
5. Final determination of the suitability of any information is the sole responsibility of the user.
6. Refer to separate sheets for fixing instructions and packing dimensions.